Technical Specification of Ink ECOO-IN-D



Туре		ECOO-IN-D							
	Printing speed: 10000rph-13000rph								
		Environment friendly							
Features		Anti-skinning performance							
	Good water/ink balance								
	Rich in printing layer								
	Clear and complete in printing dots								
	Quick-drying performance, quick setting, quick turn								
Packing		1kg/vacuum tin, 12tins/carton							
Shelf Life		3 years(from the production date); product against light and water							
	ECOO-IN-D printing ink is developed by the latest European technology system. It is made from								
	polymeric, high-soluble resin and newly-invented paste pigment. This product is suitable for printing								
Application	packaging, advertisement, label, high-quality brochures and decorative products on art paper, coated								
	paper, offset paper, cardboard, etc., especially suitable for medium and high-speed printing.								
ITEM/TYPE	TACK	FLUIDITY	PARTICLE	GLOSS	SETTING	DRYING	SKINNING		
	VALUE	(mm)	SIZE (μm)		TIME (min)	TIME (hr)	TIME (hr)		
		<u> </u>			<u> </u>				

ITEM/TYPE	TACK VALUE	FLUIDITY (mm)	PARTICLE SIZE (μm)	GLOSS	SETTING TIME (min)	DRYING TIME (hr)	SKINNING TIME (hr)
D	8-9	39±1	12.5	85	4	< 8-10	>20
YELLOW							
D	8.5-9.5	40±1	12.5	75	4	< 8-10	>20
MAGENTA							
D	8.5-9.5	39±1	12.5	75	4	< 8-10	>20
CYAN							
D	9-10	38±1	12.5	80	4	< 8-10	>20
BLACK							
Tack Value	The value is measured in 1 minute by inkometer at 32 $^{\circ}\mathrm{C}^{\circ}$ and 400rpm.						
Set Time	Printing adapter, 157g art paper, the volume of ink-coating can be up to 0.125cc.						

Condition of test Room temperature 25 ℃, humidity 65%-75%

ITEM/TYPE	Light	Heat	Acid	Alkaline	Alcohol	Soap	
	Resistance	Resistance	Resistance	Resistance	Resistance	Resistance	
D	3-4	5	5	4	4	4	
YELLOW							
D	3-4	5	5	5	4	5	
MAGENTA							
D	6-7	5	5	5	5	5	
CYAN							
D	6-7	5	5	5	5	5	
BLACK							
Light Fastness	1-8 (weak-strong)						
Others	1-5 (weak-strong)						

Hangzhou EcooGraphix Digital Technology Co, Ltd.

Add: Room 708, Tianheng Building, No.1509, Binsheng Rd, Binjiang District, Hangzhou, China

Tel: 0086 571-87391001 Fax:0086 0571-81391066

E-mail:info@ecoographix.com Website: www.ecoographix.com